

Appln No. 10/591,516
Amdt date October 25, 2011
Reply to Office action of July 25, 2011

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A resin pulley molded with a phenol resin molding material, the pheol resin molding material comprising 100 parts by weight of a resol type phenol resin, 40 to 100 parts by weight of an inorganic fiber, 30 to 90 parts by weight of a natural silica powder having an average particle size of 0.5 to 15 μm and subjected to a coupling agent treatment and 1 to 15 parts by weight of a rubber component as main components.

2. (Currently Amended) A resin pulley molded with a phenol resin molding material, the pheol resin molding material comprising 100 parts by weight of a resol type phenol resin, 40 to 100 parts by weight of an inorganic fiber, 30 to 90 parts by weight of a natural silica powder having an average particle size of 0.5 to 15 μm and subjected to a coupling agent treatment and 1 to 15 parts by weight of a rubber component as main components, wherein the inorganic fiber contains 50% by weight or more of a glass fiber.

3. (Currently Amended) A resin pulley molded with a phenol resin molding material, the pheol resin molding material comprising 100 parts by weight of a resol type phenol resin, 40 to 100 parts by weight of an inorganic fiber, 30 to 90 parts by weight of a natural silica powder having an average particle size of 0.5 to 15 μm and subjected to a coupling agent treatment and 1 to 15 parts by weight of a rubber component as main components, wherein the natural silica powder has a crushed shape.

4. (Currently Amended) A resin pulley molded with a phenol resin molding material, the pheol resin molding material comprising 100 parts by weight of a resol type phenol resin, 40 to

Appln No. 10/591,516
Amdt date October 25, 2011
Reply to Office action of July 25, 2011

100 parts by weight of an inorganic fiber, 30 to 90 parts by weight of a natural silica powder having an average particle size of 0.5 to 15 μm and subjected to a coupling agent treatment and 1 to 15 parts by weight of a rubber component as main components, wherein the inorganic fiber contains 50% by weight or more of a glass fiber and the natural silica powder has a crushed shape.

5. (Canceled).